

119 Lurgan Ave, Suite C Shippensburg, PA 17257 PHONE: 717.300.1311

EMAIL: i@needrubbernow.com www.americanmaterialsupply.com





## ACETAL

NAME:	ACETAL
	Homopolymer Acetal (polyoxymethylene)

Room temperature strength, stiffness, and tough.

Chemically resistant to many fuels and solvents

Good wear and abrasion

TENSILE STRENGTH: 10,000 PSI

FLEXURAL MODULUS: 420,000 PSI

IZOD IMPACT (NOTCHED): 1.5 ft-lbs/in of notch

WATER ABSORPTION: .25%

COEFFICIENT OF LINEAR THERMAL EXPANSION: 6.8 in/in/°Fx10-5

MAX CONTINUOS TEMP: 185 F° NO LOW TEMP TESTED

|<<<<

<<<< TEMPERATURE

## **AUTOMOTIVE & ELECTRIC**

\*\*\*Our rubber products are blended of various polymers formulated to meet stated physical specifications.

Recommendations made by American Material Supply in its product literature relating to applications of the rubber are believed to be reliable, but we make no warranty of results to be obtained since the conditions of the end application by Buyer and others are beyond American Material Supply's control.\*\*\*