

119 Lurgan Ave, Suite C Shippensburg, PA 17257 PHONE: 717.300.1311

EMAIL: i@needrubbernow.com www.americanmaterialsupply.com





## PHENOLIC CE

NAME: PHENOLIC CE

COTTON, CANVAS IMPREGNATED PHENOL

TENSILE STRENGTH(psi): 10,000

COMPRESSIVE STRENGTH(psi): 36,000

FLEXURAL STRENGTH(psi): 17,000

HARDNESS, M SCALE: 105

SHEAR STRENGTH(psi): 14,000

DIELECTRIC CONSTANT

 $10^6$  (CYCLES CONDITION A): 5.5

WATER ABSORPTION %-24 HRS: 2.0

COEFFICIENT THERMAL EXPANSION: 2.0

in/in/°C x 10-5

MAX CONTINUOS TEMP: 257 F°

FLAMMABILITY: UL94HB

<<<< TEMPERATURE

**CANVAS PHENOLIC** 

\*\*\*Our rubber products are blended of various polymers formulated to meet stated physical specifications.

Recommendations made by American Material Supply in its product literature relating to applications of the rubber are believed to be reliable, but we make no warranty of results to be obtained since the conditions of the end application by Buyer and others are beyond American Material Supply's control.\*\*\*