

119 Lurgan Ave, Suite C Shippensburg, PA 17257 PHONE: 717.300.1311

EMAIL: i@needrubbernow.com www.americanmaterialsupply.com





G11 SHEET

NAME:	G11	
	EPOXY FIBERGLASS SHEET	

TENSILE STRENGTH(psi): 37,000
COMPRESSIVE STRENGTH(psi): 63,000
FLEXURAL STRENGTH(psi): 75,000
HARDNESS, M SCALE: 112
SHEAR STRENGTH(psi): 22,000
DIELECTRIC CONSTANT
10^6 (cycles condition A): 5.0
WATER ABSORPTION %-24 HRS: .20
COEFFICIENT THERMAL EXPANSION: 1.10
in/in/°C x 10-5

MAX CONTINUOS TEMP: 356 F° <><< **TEMPERATURE** FLAMMABILITY: UL94VO

EPOXY GLASS LAMINATE

***Our rubber products are blended of various polymers formulated to meet stated physical specifications.

Recommendations made by American Material Supply in its product literature relating to applications of the rubber are believed to be reliable, but we make no warranty of results to be obtained since the conditions of the end application by Buyer and others are beyond American Material Supply's control.***